





**BUREAU
 VERITAS**

N° CE-1370-PED-F-FAB 036-16-ITA

Numero di serie / Serial number: from 16/0033/001 to 16/0033/102 [excluded cylinder(s) : none]

Limiti essenziali minimi/massimi ammissibili / Essential minimum/maximum allowable limits:


PS(bar) = 200 bar @15°C TS(°C) = -50° / +65°

Nell'esecuzione dell'attività finalizzata ad ommissione del presente N.A. certificato, Bureau Veritas Italia SpA si è riferita al dossier tecnico del fabbricante di seguito identificato:

For the activity carried out and for the issuance of the present certificate, Bureau Veritas Italia SpA took as reference the following manufacturer's technical book

INFORMAZIONI SUPPLEMENTARI (dove applicabili) / FURTHER INFORMATION (where applicable)

- volume V degli apparecchi a pressione (L): volume V of the pressure equipment (L)	5.0 Liters
- dimensione nominale della tubazione DN: nominal size for piping DN	N.A.
- pressione di prova PT applicata (bar) e data: test pressure PT applied (bar) and date	318 bar performed on 11th January 2016
- pressione di taratura del dispositivo di sicurezza (bar): safety device set pressure (bar)	N.A.
- potenza dell'attrezzatura a pressione (kW): output of the pressure equipment (kW)	N.A.
- tensione di alimentazione (volts): supply voltage (volts)	N.A.
- utilizzo previsto: intended use	breathing equipment
- rapporto di riempimento (kg/L): filling ratio (kg/L)	N.A.
- massa di riempimento massima (kg): maximum filling mass (kg)	N.A.
- tara (kg): tare mass (kg)	tare for each cylinder is indicate on manufacturer's list
- gruppo del fluido: fluid group	Group 2 (UN 1002 - Compressed Air)
- altre informazioni: other information	see operating instructions of cylinders.
Natura ed ubicazione della marcatura dell'attrezzatura: Nature and location of the affixing of the marking of the equipment	Mandatory markings on cylinders shoulder. Other eventual markings on opposite side

Fatto a Made at	Il (gg/mm/aaaa) On (dd/mm/yyyy)	Approvato e Registrato in Approved and Recorded in	Firmato da Signed by	Firma autorizzata dall'Organismo Notificato N 1370 Signature Authorized by Notified Body No 1370
PADUA	29/01/2016	Italy	LUCIANO ROSINA	

Codice di Registrazione / Registration Code: 2016/000262/CE-1370-PED

Il presente attestato è sottoposto alle Condizioni Generali di Vendita di Bureau Veritas Italia SpA allegati alla domanda d'intervento firmata dal richiedente.
 This certificate is subject to the terms of Bureau Veritas Italia SpA General Conditions of Service attached to the agreement signed by the applicant.

Il presente documento non può essere riprodotto parzialmente se non con l'approvazione scritta di Bureau Veritas Italia SpA e del Cliente.
 The present document shall not be reproduced, except in full, without Bureau Veritas Italia SpA and Client's approval.



The Company Faber Industrie s.p.a. – Via dell'Industria, 23 - XI Zona Industriale Cividale del Friuli (UD) – ITALY,
La società Faber Industrie s.p.a. – con sede in Via dell'Industria, 23 - XI Zona Industriale Cividale del Friuli (UD) – ITALIA,

DECLARES
DICHIARA

that the manufactured pressure equipment:
che l'attrezzatura a pressione costruita:

Definition: **CYLINDER FOR BREATHING APPARATUS**
Definizione: **BOMBOLE PER APPARECCHIO RESPIRATORE**

Water capacity V **5** litre/ litri
Capacità

Operating fluid: **1002 AIR**
Fluido contenuto:

Manufacturer N°/ N° di fabbrica

from/ dal **16/0033/001** to/ al **16/0033/102**

Drawing N°: **EN-140-318-890 REV0**
N° disegno:

Min. e max. allowable temperatures: **-50 + +65 °C**
Temperatura min. e max. ammissibili:

Max. allowable pressure: **200** bar
Pressione max. ammissibile.

No. of cylinders / numero di bombole

98

MEETS THE REQUIREMENTS OF DIRECTIVE 97/23/CE
E' CONFORME AI REQUISITI DELLA DIRETTIVA 97/23/CE

1. Conformity assessment procedures used: Module **B+F** (Category **III**) (Reference to Annex II and III of Directive 97/23/CE)
*Procedura/e di valutazione di conformità utilizzata: Modulo **B+F** (Categoria **III**) (Riferimento allegati II e III della Direttiva 97/23/CE)*
2. Notified Body charged of the conformity assessment: N° **1370 BUREAU VERITAS ITALIA**
Organismo Notificato incaricato della valutazione di conformità: N°
3. Registration number of "CE Type Examination Certificate": **CE-1370-PED-B-FAB007-12-ITA**
Estremi dell'Attestato dell'esame CE del tipo:
4. Not harmonized standards applied to designing and manufacture: **EN 1964-1:1999**
Norme non armonizzate applicate alla progettazione ed alla costruzione:
5. Harmonized standards applied to designing and manufacture: **None**
*Norme armonizzate applicate alla progettazione ed alla costruzione: **Nessuna***
6. Others European Directives applied to the equipment: **None**
*Eventuali altre Direttive europee applicate all'attrezzatura: **Nessuna***
7. Registration number of Conformity Certificate issued by the Notified Body charged of assessment procedure
"Module F": **CE-1370-PED-F-FAB 036-16-ITA**
Estremi dell'Attestato di Conformità rilasciato dall'Organismo Notificato incaricato della procedura di valutazione "Modulo F":

It is declared that the equipment has been hydraulic tested with favourable result at the pressure of: (PT) **318** bar, it is marked **CE 1370** and with identification data and the working parameters upside reported.

*Dichiara inoltre che l'attrezzatura è stata sottoposta con esito favorevole a prova di pressione idraulica di: (PT) **318** bar, che è stata marcata **CE 1370** e con i dati identificativi e le caratteristiche di esercizio sopra riportati.*

The assembly must be subjected to a global conformity assessment procedure described in the directive PED 97/23/CE.
L'insieme deve essere sottoposto ad una procedura globale di valutazione di conformità così come previsto dalla direttiva PED 97/23/CE.

Cividale del Friuli 01/02/2016

Faber Industrie S.p.A.

Manufacturer: **FABER INDUSTRIE SPA - CIVIDALE DEL FRIULI - UDINE- ITALY**
 Inspection: **BUREAU VERITAS** Specification: **EN 1964-1:1999 (PED)**
 Customer: **Aerotecnica Coltri S.p.A.**
 Owner stamping: **COLTRI SUB**
 Manufacturer serial No. :
 From **16/0033/001** to **16/0033/102**

Gas: **1002 AIR**

Total cylinders: **98**
 Type of cylinder: **Seamless steel gas cylinders**
 Material: **34CRMO4**

Working pressure at 15° C: **200 bar**
 Working temperature: **-50° + +65° C**

Nominal data

Drawing no.	Test Pressure (bar)	Minimum Thickness		Nominal Diameter (mm)	Nominal Length without valve (mm)	Nominal Water Capacity (l)	Nominal Weight (Kg)
		wall (mm)	base (mm)				
EN-140-318-890 REV0	318	3.1	3.1	140	440	5	5.7

We hereby certify that the cylinders of the batch no. **16/0033** comply with the following requirements

Manufacturing process: cylinders manufactured from **plate**

Neck thread : **M25X2 EN 144-1 2000**

Identification marks stamped on cylinders shoulder according to drawing: **PPED004 2**

Minimum cylindrical shell thickness:

The wall thickness of all cylinders has been measured and found to be not less than : **3.1 mm**

Hardness range:

All cylinders have been controlled within the following hardness values: **Min 306 HB, Max 333 HB**

Heat treatment:

All cylinders have been heat treated at the following temperatures:

Liquid quench: **900 °C ± 20 °C**

Temper at: **570 °C ± 30 °C**

Chemical analysis:

Material: **34CRMO4**

The cylinders of the batch no. **16/0033** have been manufactured from the following cast(s) of steel:

Cast Numb.	Code (*)	C (%)	Si (%)	Mn (%)	P (%)	S (%)	Cr (%)	Mo (%)	S+P (%)
18888	DJU	0.35	0.22	0.72	0.008	0.000	1.13	0.22	0.008

(*)marked on outer bottom surface

Date: 01/02/2016	For and on behalf of the manufacturer:  Faber INDUSTRIE S.p.A. Cividale del Friuli	For and on behalf of B.V. ITALY WITNESSED - NOTED - REVIEWED SURVEYOR E. BUEFON DATE
-------------------------	--	---



MEASUREMENTS OF SAMPLE CYLINDERS:

Cylinder Serial no.	Water Capacity (L)	Empty Weight (Kg)	Minimum measured thickness	
			of the wall (mm)	of the base (mm)
16/0033/101	5	6.06	3.5	6.4
16/0033/102	5	6.01	3.5	6.4

MECHANICAL TESTS CARRIED OUT ON SAMPLE CYLINDERS:

Cylinder Serial no.	Code (*)	Test piec dimension (mm)	Yield strength (MPa)	Tensile strength (MPa)	Elongation (%)	Impact test -50°C			Bend test 180° without cracking		
						Direction	Individual (J/cm ²)			Mean (J/cm ²)	
16/0033/101	DJU	10.0 x 3.6	899	1054	15.4	LONG	83	83	90	86	SATISF.
Minimum values specified			890	990	14		48		60		

BURST TESTS CARRIED OUT ON SAMPLE CYLINDERS:

Cylinder Serial no.	Code (*)	Hydraulic burst test bar	Description of the fracture
16/0033/102	DJU	591	LONGITUDINAL
Minimum values specified		509	

For and on behalf of the manufacturer:

[Signature]
Faber
INDUSTRIE S.p.A.
Cividale del Friuli

For and on behalf of A.I.A.



TESTING OBJECT:

CYLINDER ACCORDING TO DRAWING: EN-140-318-890 REV0
OUTSIDE DIAMETER: 140 mm WATER CAPACITY: 5 l
MIN. WALL THICKNESS: 3.1 mm NOMINAL LENGTH: 440 mm
FROM CYLINDER SERIAL No.: 16/0033/001 to 16/0033/102

TEST TECHNICAL DATA:

EXAMINATION STANDARD: EN 1964-1
INSPECTED PART: CYLINDRICAL WALL
EXTENTION OF EXAMINATION: 100 %
FABRICATION STAGE: AFTER HEAT TREATMENT (QUENCHING AND TEMPERING), SHOT BLASTING
AND BEFORE PRESSURE TESTING
PROBES: LONGITUDINAL, TRANSVERSAL AND THICKNESS
COUPLANT: EMULSIFIED WATER
SCANNING DIRECTION: CIRCUMFERENTIAL, AXIAL AND RADIAL DIRECTIONS
REFERENCE REFLECTOR: CALIBRATION CYLINDER ACCORDING TO EN 1964-1

EXAMINATION RESULTS:

ALL CYLINDERS HAVE BEEN CHECKED GIVING SATISFACTORY RESULTS.

For and on behalf of the manufacturer:

[Signature]
Faber
INDUSTRIE S.p.A.
Civita del Trivoli

For and on behalf of A.I.A.



LOT No. 16/0033 NUMBER OF CYLINDERS: 98 TEST DATE: 01/2016

ACCORDING TO DWG.: EN-140-318-890 REV0

WORKING PRESSURE AT 15° C. 200 bar

CYLINDER SIZE : OUTSIDE DIAMETER 140 mm LENGTH 440 mm

REMARKS: M = Mechanical Tests, B = Burst Tests, P = Prototype Tests, S = Cylinder Discarded, C = Cycling Test.

C+B = Cycling + Burst Test.

FITTINGS : "CO" = Collar

CYLINDER SERIAL No.	CUSTOMER NUMBER	HEAT CODE AND NUMBER	TEST PRESSURE (bar)	CYLINDER WATER CAPACITY (l)	FITTINGS	MASS (Kg)	TARE (Kg)	REMARKS
16/0033/001		DJU 18888	318	5.0		6.06		
16/0033/002		DJU 18888	318	5.0		6.05		
16/0033/003		DJU 18888	318	5.0		6.06		
16/0033/004		DJU 18888	318	5.0		6.05		
16/0033/005		DJU 18888	318	5.0		6.01		
16/0033/006		DJU 18888	318	5.0		6.11		
16/0033/007		DJU 18888	318	5.0		6.04		
16/0033/008		DJU 18888	318	5.0		6.05		
16/0033/009		DJU 18888	318	5.0		6.10		
16/0033/010		DJU 18888	318	5.0		6.11		
16/0033/011		DJU 18888	318	5.0		6.07		
16/0033/012		DJU 18888	318	5.0		6.05		
16/0033/013		DJU 18888	318	5.0		6.12		
16/0033/014		DJU 18888	318	5.0		6.04		
16/0033/015		DJU 18888	318	5.0		6.02		
16/0033/016		DJU 18888	318	5.0		6.04		
16/0033/017		DJU 18888	318	5.0		6.04		
16/0033/018		DJU 18888	318	5.0		6.04		
16/0033/019		DJU 18888	318	5.0		6.06		
16/0033/020		DJU 18888	318	5.0		6.04		
16/0033/021		DJU 18888	318	5.0		6.04		
16/0033/022		DJU 18888	318	5.0		6.06		
16/0033/023		DJU 18888	318	5.0		6.08		
16/0033/024		DJU 18888	318	5.0		6.03		
16/0033/025		DJU 18888	318	5.0		6.08		
16/0033/026		DJU 18888	318	5.0		6.09		
16/0033/027		DJU 18888	318	5.0		6.07		
16/0033/028		DJU 18888	318	5.0		6.06		
16/0033/029		DJU 18888	318	5.0		6.06		
16/0033/030		DJU 18888	318	5.0		6.04		
16/0033/031		DJU 18888	318	5.0		6.05		
16/0033/032		DJU 18888	318	5.0		6.04		
16/0033/033		DJU 18888	318	5.0		6.07		
16/0033/034		DJU 18888	318	5.0		6.05		
16/0033/035		DJU 18888	318	5.0		6.05		
16/0033/036		DJU 18888	318	5.0		6.06		
16/0033/037		DJU 18888	318	5.0		6.06		
16/0033/038		DJU 18888	318	5.0		6.09		
16/0033/039		DJU 18888	318	5.0		6.09		
16/0033/040		DJU 18888	318	5.0		6.10		

Manufacturer stamp and signature:

[Signature]
Faber
 INDUSTRIE S.p.A.
 Cividale del Friuli

A.I.A. stamp and signature:



LOT No. 16/0033 NUMBER OF CYLINDERS: 98 TEST DATE: 01/2016

ACCORDING TO DWG.: EN-140-318-890 REV0

WORKING PRESSURE AT 15° C: 200 bar

CYLINDER SIZE : OUTSIDE DIAMETER 140 mm LENGTH 440 mm


REMARKS: M = Mechanical Tests, B = Burst Tests, P = Prototype Tests, S = Cylinder Discarded, C = Cycling Test,

C+B = Cycling + Burst Test.

FITTINGS : "CO" = Collar

CYLINDER SERIAL No.	CUSTOMER NUMBER	HEAT CODE AND NUMBER	TEST PRESSURE (bar)	CYLINDER WATER CAPACITY (l)	FITTINGS	MASS (Kg)	TARE (Kg)	REMARKS
16/0033/041		DJU 18888	318	5.0		6.07		
16/0033/042		DJU 18888	318	5.0		6.10		
16/0033/043		DJU 18888	318	5.0		6.06		
16/0033/044		DJU 18888	318	5.0		6.08		
16/0033/045		DJU 18888	318	5.0		6.06		
16/0033/046		DJU 18888	318	5.0		6.08		
16/0033/047		DJU 18888	318	5.0		6.09		
16/0033/048		DJU 18888	318	5.0		6.07		
16/0033/049		DJU 18888	318	5.0		6.11		
16/0033/050		DJU 18888	318	5.0		6.09		
16/0033/051		DJU 18888	318	5.0		6.05		
16/0033/052		DJU 18888	318	5.0		6.04		
16/0033/053		DJU 18888	318	5.0		6.06		
16/0033/054		DJU 18888	318	5.0		6.09		
16/0033/055		DJU 18888	318	5.0		6.07		
16/0033/056		DJU 18888	318	5.0		6.04		
16/0033/057		DJU 18888	318	5.0		6.09		
16/0033/058		DJU 18888	318	5.0		6.06		
16/0033/059		DJU 18888	318	5.0		6.08		
16/0033/060		DJU 18888	318	5.0		6.04		
16/0033/061		DJU 18888	318	5.0		6.10		
16/0033/062		DJU 18888	318	5.0		6.08		
16/0033/063		DJU 18888	318	5.0		6.08		
16/0033/064		DJU 18888	318	5.0		6.10		
16/0033/065		DJU 18888	318	5.0		6.08		
16/0033/066		DJU 18888	318	5.0		6.10		
16/0033/067		DJU 18888	318	5.0		6.08		
16/0033/068		DJU 18888	318	5.0		6.11		
16/0033/069		DJU 18888	318	5.0		6.09		
16/0033/070		DJU 18888	318	5.0		6.09		
16/0033/071		DJU 18888	318	5.0		6.03		
16/0033/072		DJU 18888	318	5.0		6.06		
16/0033/073		DJU 18888	318	5.0		6.06		
16/0033/074		DJU 18888	318	5.0		6.04		
16/0033/076		DJU 18888	318	5.0		6.11		
16/0033/077		DJU 18888	318	5.0		6.08		
16/0033/078		DJU 18888	318	5.0		6.03		
16/0033/079		DJU 18888	318	5.0		6.08		
16/0033/080		DJU 18888	318	5.0		6.04		
16/0033/081		DJU 18888	318	5.0		6.08		

Manufacturer stamp and signature:


Faber
 INDUSTRIE S.p.A.
 Cavale del Friuli

A.I.A. stamp and signature:



LOT No. 16/0033 NUMBER OF CYLINDERS: 98 TEST DATE: 01/2016

ACCORDING TO DWG: EN-140-318-890 REV0

WORKING PRESSURE AT 15° C: 200 bar

CYLINDER SIZE: OUTSIDE DIAMETER 140 mm LENGTH 440 mm

REMARKS: M = Mechanical Tests, B = Burst Tests, P = Prototype Tests, S = Cylinder Discarded, C = Cycling Test,

C+B = Cycling + Burst Test.

FITTINGS: "CO" = Collar

CYLINDER SERIAL No.	CUSTOMER NUMBER	HEAT CODE AND NUMBER	TEST PRESSURE (bar)	CYLINDER WATER CAPACITY (l)	FITTINGS	MASS (Kg)	TARE (Kg)	REMARKS
16/0033/082		DJU 18888	318	5.0		6.07		
16/0033/083		DJU 18888	318	5.0		6.05		
16/0033/084		DJU 18888	318	5.0		6.05		
16/0033/085		DJU 18888	318	5.0		6.04		
16/0033/086		DJU 18888	318	5.0		6.09		
16/0033/087		DJU 18888	318	5.0		6.08		
16/0033/088		DJU 18888	318	5.0		6.05		
16/0033/089		DJU 18888	318	5.0		6.04		
16/0033/090		DJU 18888	318	5.0		6.07		
16/0033/091		DJU 18888	318	5.0		6.08		
16/0033/092		DJU 18888	318	5.0		6.07		
16/0033/093		DJU 18888	318	5.0		6.05		
16/0033/094		DJU 18888	318	5.0		6.05		
16/0033/096		DJU 18888	318	5.0		6.12		
16/0033/097		DJU 18888	318	5.0		6.06		
16/0033/098		DJU 18888	318	5.0		6.08		
16/0033/099		DJU 18888	318	5.0		6.06		
16/0033/100		DJU 18888	318	5.0		6.07		

Manufacturer stamp and signature:

Faber
INDUSTRIE S.p.A.
Candole del Friuli

A.I.A. stamp and signature:



Istruzioni operative per il montaggio, la messa in servizio, l'impiego, la manutenzione e le visite periodiche delle bombole in acciaio per auto-respiratori subacquei (PED 97/23/CE).

-La bombola per l'apparecchio respiratore è soggetta ai regolamenti e alle norme per l'uso, manutenzione e le ispezioni periodiche, vigenti nel paese in cui viene utilizzata. E' responsabilità del proprietario della bombola eseguire le visite periodiche siano entro i termini prefissati. Si raccomanda di sottoporre la bombola ad un controllo visivo interno ed esterno da personale competente almeno una volta l'anno.

-L'insieme (costituito da varie attrezzature a pressione montate per costruire un tutto integro e funzionale "apparecchio respiratore") deve soddisfare i requisiti essenziali di sicurezza di cui all'allegato I della direttiva PED 97/23/CE.

-L'insieme deve essere sottoposto ad una procedura globale di valutazione di conformità così come previsto dalla direttiva PED 97/23/CE.

-E' di importanza vitale avere sempre estrema attenzione alla cura e alla manutenzione della bombola per respiratori subacquei. E' essenziale che il respiratore subacqueo sia accuratamente esaminato per verificare l'eventuale presenza di danneggiamenti o difetti dopo ogni utilizzo. Tutti i difetti devono essere eliminati prima che il respiratore subacqueo venga di nuovo utilizzato. La mancanza di cura durante la manipolazione, con attrezzatura impropria, può non solo innescare difetti pericolosi, ma rendere le successive manutenzioni costose o addirittura impossibili.

- Le bombole devono essere manipolate con cura non devono essere fatte cadere. Quando trasportate devono essere bloccate in maniera sicura in modo tale che non si muovano durante il trasporto.

-Le condizioni della superficie interna delle bombole possono essere mantenute integre solo se la superficie interna rimane sempre asciutta. La bombola deve essere caricata con aria secca (contenuto d'acqua < 50 mg/m³ per una pressione di carica di 200 bar e contenuto d'acqua < 35mg/m³ per una pressione di carica maggiore di 200 bar, secondo EN12021) e non deve mai essere completamente scaricata in quanto dell'acqua potrebbe essere risucchiata all'interno della bombola contaminandola.

Operating instructions for the mounting, putting into service, use, maintenance and periodic inspection of Faber Steel Cylinders for Scuba Diving (PED 97/23/CE).

-The cylinder for breathing apparatus is subjected to the national regulations and standards for the use, maintenance and periodic inspection, in force in the country of use. The owner of pressure equipment is responsible that periodical inspections are carried out as required by the national regulation and standards. It is recommended that the cylinder will be inspected visually (internally and externally) by a competent person at least annually.

-The assembly (that means several pieces of pressure equipment assembled to constitute an integrated and functional whole "breathing apparatus") must satisfy the essential safety requirements set out in Annex I of the directive PED 97/23/CE.

-The assembly shall be subjected to a global conformity assessment procedure described in the directive PED 97/23/CE.

-Strict attention to care and maintenance of all types of breathing apparatus used underwater is of vital importance at all times.

It is essential that the complete equipment be thoroughly examined for damage or defect before and after every occasion on which it is used. All defects should be rectified before the equipment is used again. Careless manipulation with inappropriate tools may not only give rise to dangerous defects, but render further maintenance expensive or impossible.

- Cylinders should be handled with care and should not be dropped. When being transported they should be firmly secured so that they cannot move about.

- The condition of the inside of the cylinder can be maintained by keeping it dry at all times. The cylinder should be filled with dry air (Water content <50 mg/m³ for a charging pressure of 200 bar and water content < 35mg/m³ for a charging pressure greater than 200 bar, as for EN12021), and never completely discharged as this can lead to water getting back into the cylinder and causing contamination.

Le bombole devono essere immagazzinate, preferibilmente in posizione verticale, in un posto fresco, secco e lontano da fonti di calore.

-Dopo l'uso, soprattutto in acqua di mare, dalla bombola devono essere tolti le cinghie e il fondello e accuratamente lavata con acqua dolce al fine di rimuovere le tracce di acqua salata e lo sporco, specialmente dalle cavità e poi asciugata. Prima dell'immagazzinamento, o quando la bombola è stata completamente scaricata e l'acqua di mare può essere entrata nella bombola, la valvola deve essere rimossa dalla bombola e la bombola deve essere lavata internamente ed esternamente con acqua dolce e accuratamente asciugata. Questa operazione deve essere normalmente fatta da personale competente. Mai svitare o rimuovere la valvola con la bombola in pressione. La bombola non deve essere immagazzinata con la valvola rivolta all'ingiù. L'azione corrosiva dell'acqua di mare non deve essere mai sottovalutata, se non vengono prese opportune precauzioni per la pulizia delle bombole dopo l'utilizzo, seri danni potranno essere arrecati alla bombola durante il periodo in cui rimarrà inutilizzata. Anche se si fanno immersioni in acqua dolce, ci possono essere delle sostanze corrosive in soluzione quali rifiuti chimici e oleosi che non sono visibili al momento, ma che possono innescare una azione corrosiva se lasciate a contatto con la bombola.

- La verniciatura, la metallizzazione e i componenti devono essere mantenuti in buone condizioni. Abrasioni e graffi delle bombole devono essere evitate. Per la rimozione della vernice non devono essere utilizzati metodi chimici o a caldo. Zone di corrosione della bombola possono essere eliminate solo secondo le normative nazionali applicabili (Es.: BS 5430). Dopo la necessaria preparazione, la bombola può essere riverniciata. La bombola non deve essere modificata in nessuna circostanza. Questo può comportare seri indebolimenti della bombola e portare ad incidenti. La filettatura della bombola non deve essere alterata in alcun modo. Boccole o adattatori non devono essere utilizzati. Se la bombola non viene utilizzata per un lungo periodo di tempo si raccomanda che debba essere vista da personale competente per essere scaricata e successivamente ricaricata con una leggera pressione positiva. Se la bombola non viene ricaricata subito, deve essere lasciata con la valvola chiusa. Una bombola che è risultata scarta all'ispezione deve essere resa inutilizzabile da personale competente.

Cylinders should be stored, preferably in the vertical position, in a cool, dry place and away from excessive heat.

-After use, particularly in seawater, the outside surface of the cylinder should be removed from its harness and boot and then washed in clean, fresh water to remove all traces of salt water and dirt, especially from any crevices and then dried.

Before storage, or when the cylinder has been completely discharged and seawater may have entered the cylinder, the cylinder valve should be removed and the cylinder washed internally and externally in clean fresh water and thoroughly dried. This operation should normally be undertaken by a competent person. Never unscrew or remove the valve when the cylinder is under pressure.

The cylinder should not be stored with the valve downwards.

The corrosion action of seawater and water-borne contaminants should never be underestimated, and if precautions are not taken to clean the apparatus properly after use, serious damage may be caused to all parts of the apparatus while it is stowed away. Even when diving in apparently fresh water, there may be corrosive substances in solution such as chemical and petroleum wastes which are not noticeable at the time, but which will start corrosive action if left in contact with the apparatus.

- The paintwork, metal spray undercoating and fittings should be kept in good condition. Scratching of cylinders should be avoided. Heat or chemical process may not be used to remove old paint. Corrosion on cylinders should also be removed in accordance with national standards in force in the country of use (Eg.: BS 5430). After the necessary preparation, cylinders should be re-painted. Cylinders should not be modified under any circumstance. This may result in serious weakening of cylinder and lead to accident. The threads in the cylinder neck should not be altered in any way. Bushes or adapters should not be used. If the cylinder is not required for a long period it is recommended that it be returned to a competent person for discharging, removal of the valve, extraction of any oil or water, drying out and refitting of the valve. The cylinder should then be recharged to a slight positive pressure. If the cylinder is not to be recharged immediately, it should be left with the valve closed. A cylinder that has failed on inspection should be left with a competent person who will then destroy it.

- La ricarica deve essere fatta solo con idonei impianti che assicurino che l'aria compressa sia esente da umidità, olio e altre impurità, e che è adeguata all'utilizzo per respiratori subacquei.

Mai caricare ossigeno o altri gas diversi dall'aria nelle bombole per aria.

Prima della carica della bombola, è responsabilità della ditta o persona che esegue la carica verificare che la bombola sia conforme ai regolamenti nazionali in vigore.

E' essenziale che le bombole siano caricate con attenzione e lentamente al fine di prevenire sovraccariche e surriscaldamenti, e che la pressione di carica sia tale che, dopo raffreddamento a temperatura ambiente, la pressione di carica della bombola non sia superata.

La pressione di esercizio massima ammissibile a 15°C ed espressa in bar è punzonata sulla bombola. Sovraccaricare le bombole è altamente pericoloso. L'identificazione della sigla della filettatura della bombola è punzonata sulla bombola. Utilizzare valvole con filettatura diversa è vietato perché altamente pericoloso.

- Recharging should be undertaken only with proper equipment that ensures that the compressed air is free from moisture, oil and other impurities, and is fit for breathing purposes. Never put oxygen or any gas, other than air, in an air cylinder.

Before recharging a cylinder, it is the responsibility of the gas compressing firm or person to ensure that the cylinder complies with statutory regulations.

It is essential that cylinders be charged carefully and slowly to prevent overcharging and overheating, and that the charging pressure be such that, after cooling to ambient temperature, the maximum allowable pressure for the cylinder is not exceeded.

The maximum allowable pressure at 15°C, in bar, is stamped on the cylinder.

Overcharging of cylinders is highly dangerous.

The identification code of the neck tread is stamped on the cylinder. Use of valves with different threads are forbidden because highly dangerous.